



Claims


1. A polyolefin composition which comprises as UV absorber a mixture of
- at least one hydroxybenzophenone and at least one 2-hydroxyphenylbenzotriazole with the proviso that the polyolefin is a high density polyethylene of the "Phillips" type or a polyethylene of the metallocene type;
 - at least one hydroxybenzophenone and at least one 2-hydroxyphenyltriazine, with the proviso that if the polyolefin is polypropylene, no polyvinylpyridin is present
 - at least one hydroxybenzophenone and at least one oxanilide;
 - at least one 2-hydroxyphenylbenzotriazole and at least one oxanilide;
 - at least one 2-hydroxyphenyltriazine and at least one oxanilide;
 - at least one hydroxybenzophenone, at least one 2-hydroxyphenylbenzotriazole and at least one oxanilide;
 - at least one hydroxybenzophenone, at least one oxanilide and at least one 2-hydroxyphenyltriazine; or
 - at least one 2-hydroxyphenylbenzotriazole, at least one oxanilide and at least one 2-hydroxyphenyltriazine.
2. A polyolefin composition according to claim 1 wherein the polyolefin is polyethylene or polypropylene.
3. A polyolefin composition according to claim 1 wherein the hydroxybenzophenone is of formula I




the 2-hydroxyphenylbenzotriazole is of formula IIa, IIb or IIc



(IIb)




(IIa),




(IIc) ;

the 2-hydroxyphenyltriazine is of formula III



(III);

and the oxanilide is of formula (IV)



(IV) ; wherein


4403360

SUB
a1

in the compounds of the formula (I) v is an integer from 1 to 3 and w is 1 or 2 and the substituents Z independently of one another are hydrogen, halogen, hydroxyl or alkoxy having 1 to 12 carbon atoms;

in the compounds of the formula (IIa),

R₁ is hydrogen, alkyl having 1 to 24 carbon atoms, phenylalkyl having 1 to 4 carbon atoms in the alkyl moiety, cycloalkyl having 5 to 8 carbon atoms or a radical of the formula



R₄ and R₅ independently of one another are alkyl having in each case 1 to 5 carbon atoms, or R₄, together with the radical C_nH_{2n+1-m}, forms a cycloalkyl radical having 5 to 12 carbon atoms,

m is 1 or 2, n is an integer from 2 to 20 and

M is a radical of the formula -COOR₆ in which

R₆ is hydrogen, alkyl having 1 to 12 carbon atoms, alkoxyalkyl having in each case 1 to 20 carbon atoms in the alkyl moiety and in the alkoxy moiety or phenylalkyl having 1 to 4 carbon atoms in the alkyl moiety,

R₂ is hydrogen, halogen, alkyl having 1 to 18 carbon atoms, and phenylalkyl having 1 to 4 carbon atoms in the alkyl moiety, and

R₃ is hydrogen, chlorine, alkyl or alkoxy having in each case 1 to 4 carbon atoms or -COOR₆ in which R₆ is as defined above, at least one of the radicals R₁ and R₂ being other than hydrogen;

in the compounds of the formula (IIb)

T is hydrogen or alkyl having 1 to 6 carbon atoms,

T₁ is hydrogen, chlorine or alkyl or alkoxy having in each case 1 to 4 carbon atoms,


n is 1 or 2 and,

if n is 1,

T₂ is chlorine or a radical of the formula -OT₃ or $\begin{array}{c} T_4 \\ | \\ -N- \\ | \\ T_5 \end{array}$ and,

SUB 27


1991	1992	1993	1994	1995	1996	1997	1998	1999	2000	2001	2002	2003	2004	2005	2006	2007	2008	2009	2010	2011	2012	2013	2014	2015	2016	2017	2018	2019	2020	2021	2022	2023	2024	2025	2026	2027	2028	2029	2030	2031	2032	2033	2034	2035	2036	2037	2038	2039	2040	2041	2042	2043	2044	2045	2046	2047	2048	2049	2050	2051	2052	2053	2054	2055	2056	2057	2058	2059	2060	2061	2062	2063	2064	2065	2066	2067	2068	2069	2070	2071	2072	2073	2074	2075	2076	2077	2078	2079	2080	2081	2082	2083	2084	2085	2086	2087	2088	2089	2090	2091	2092	2093	2094	2095	2096	2097	2098	2099	2100	2101	2102	2103	2104	2105	2106	2107	2108	2109	2110	2111	2112	2113	2114	2115	2116	2117	2118	2119	2120	2121	2122	2123	2124	2125	2126	2127	2128	2129	2130	2131	2132	2133	2134	2135	2136	2137	2138	2139	2140	2141	2142	2143	2144	2145	2146	2147	2148	2149	2150	2151	2152	2153	2154	2155	2156	2157	2158	2159	2160	2161	2162	2163	2164	2165	2166	2167	2168	2169	2170	2171	2172	2173	2174	2175	2176	2177	2178	2179	2180	2181	2182	2183	2184	2185	2186	2187	2188	2189	2190	2191	2192	2193	2194	2195	2196	2197	2198	2199	2200	2201	2202	2203	2204	2205	2206	2207	2208	2209	2210	2211	2212	2213	2214	2215	2216	2217	2218	2219	2220	2221	2222	2223	2224	2225	2226	2227	2228	2229	2230	2231	2232	2233	2234	2235	2236	2237	2238	2239	2240	2241	2242	2243	2244	2245	2246	2247	2248	2249	2250	2251	2252	2253	2254	2255	2256	2257	2258	2259	2260	2261	2262	2263	2264	2265	2266	2267	2268	2269	2270	2271	2272	2273	2274	2275	2276	2277	2278	2279	2280	2281	2282	2283	2284	2285	2286	2287	2288	2289	2290	2291	2292	2293	2294	2295	2296	2297	2298	2299	2300	2301	2302	2303	2304	2305	2306	2307	2308	2309	2310	2311	2312	2313	2314	2315	2316	2317	2318	2319	2320	2321	2322	2323	2324	2325	2326	2327	2328	2329	2330	2331	2332	2333	2334	2335	2336	2337	2338	2339	2340	2341	2342	2343	2344	2345	2346	2347	2348	2349	2350	2351	2352	2353	2354	2355	2356	2357	2358	2359	2360	2361	2362	2363	2364	2365	2366	2367	2368	2369	2370	2371	2372	2373	2374	2375	2376	2377	2378	2379	2380	2381	2382	2383	2384	2385	2386	2387	2388	2389	2390	2391	2392	2393	2394	2395	2396	2397	2398	2399</
------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	--------



or -O-T₉-O- in which

T₃ is hydrogen, alkyl which has 1 to 18 carbon atoms and is unsubstituted or substituted by 1 to 3 hydroxyl groups or by -OCOT₆, alkyl which has 3 to 18 carbon atoms, is interrupted once or several times by -O- or -NT₆- and is unsubstituted or substituted by hydroxyl or -OCOT₆, cycloalkyl which has 5 to 12 carbon atoms and is unsubstituted or substituted by hydroxyl and/or alkyl having 1 to 4 carbon atoms, alkenyl which has 2 to 18 carbon atoms and is unsubstituted or substituted by hydroxyl, phenylalkyl having 1 to 4 carbon atoms in the

alkyl moiety, or a radical of the formula $-\text{CH}_2\text{CH}(\text{OH})-\text{T}_7$ or



T₄ and T₅ independently of one another are hydrogen, alkyl having 1 to 18 carbon atoms, alkyl which has 3 to 18 carbon atoms and is interrupted once or several times by -O- or -NT₆-, cycloalkyl having 5 to 12 carbon atoms, phenyl, phenyl which is substituted by alkyl having 1 to 4 carbon atoms, alkenyl having 3 to 8 carbon atoms, phenylalkyl having 1 to 4 carbon atoms in the alkyl moiety or hydroxyalkyl having 2 to 4 carbon atoms,

T₆ is hydrogen, alkyl having 1 to 18 carbon atoms, cycloalkyl having 5 to 12 carbon atoms, alkenyl having 3 to 8 carbon atoms, phenyl, phenyl which is substituted by alkyl having 1 to 4 carbon atoms, phenylalkyl having 1 to 4 carbon atoms in the alkyl moiety,

T₇ is hydrogen, alkyl having 1 to 18 carbon atoms, phenyl which is unsubstituted or substituted by hydroxyl, phenylalkyl having 1 to 4 carbon atoms in the alkyl moiety, or -CH₂OT₈,

T₈ is alkyl having 1 to 18 carbon atoms, alkenyl having 3 to 8 carbon atoms, cycloalkyl having 5 to 10 carbon atoms, phenyl, phenyl which is substituted by alkyl having 1 to 4 carbon atoms, or phenylalkyl having 1 to 4 carbon atoms in the alkyl moiety,

T₉ is alkylene having 2 to 8 carbon atoms, alkenylene having 4 to 8 carbon atoms, alkynylene having 4 carbon atoms, cyclohexylene, alkylene which has 2 to 8 carbon atoms and is interrupted once or several times by -O-, or a radical of the formula -CH₂CH(OH)CH₂OT₁₁, -OCH₂CH(OH)CH₂- or -CH₂-C(CH₂OH)₂-CH₂-,

T₁₀ is alkylene which has 2 to 20 carbon atoms and can be interrupted once or several times by -O-, or cyclohexylene,

T₁₁ is alkylene having 2 to 8 carbon atoms, alkylene which has 2 to 18 carbon atoms and is

[illegible]

ounds of formula (IIc)

alkyl and k is a number from 1 to 4;

ounds of the formula (III)

nd r is an integer from 1 to 3, the substituents
ntly of one another are hydrogen, hydroxyl, h
toms, alkoxy having 1 to 18 carbon atoms, or l
having 1 to 18 carbon atoms, phenoxy which is
oxy having 1 to 18 carbon atoms, or halogen,
ch case 1 to 18 carbon atoms or halogen, alkyl
stituted by -COOH, -COOY₈, -CONH₂, -CONHY,
COY₁₁, -CN and/or -OCOY₁₁, alkyl which has
y one or more oxygen atoms and is unsubstit
g 1 to 12 carbon atoms, alkenyl having 3 to 6
substituted or substituted by hydroxyl, alkyl hav
enylalkyl which has 1 to 5 carbon atoms in the
d by hydroxyl, chlorine and/or methyl, -COY₁₂
e having 2 to 16 carbon atoms, alkenylene hav
ylene which has 3 to 20 carbon atoms, is inter
stituted by hydroxyl, -CH₂CH(OH)CH₂-O-Y₁₅-
NH-CO- or -(CH₂)_m-CO₂-Y₁₈-OCO-(CH₂)_m, in w
3,
having 1 to 18 carbon atoms, alkenyl having 3 to
on atoms, is interrupted by one or more oxyge
d by hydroxyl, alkyl which has 1 to 4 carbon at
-NY₉Y₁₀ or -OCOY₁₁ and/or hydroxyl, alkenyl
phenylalkyl having 1 to 5 carbon atoms in the a
ndependently of one another are alkyl having 1

R'₂ is C₁-C₁₂alkyl and k is a number from 1 to 4;

u is 1 or 2 and r is an integer from 1 to 3, the substituents

if u is 1,


if u is 2,

Y₈ is alkyl having 1 to 18 carbon atoms, alkenyl having 3 to 18 carbon atoms, alkyl which has 3 to 20 carbon atoms, is interrupted by one or more oxygen or sulfur atoms or -NT₆- and/or is substituted by hydroxyl, alkyl which has 1 to 4 carbon atoms and is substituted by -P(O)(OY₁₄)₂, -NY₉Y₁₀ or -OCOY₁₁ and/or hydroxyl, alkenyl having 3 to 18 carbon atoms, glycidyl, or phenylalkyl having 1 to 5 carbon atoms in the alkyl moiety,


Y₉ and Y₁₀ independently of one another are alkyl having 1 to 12 carbon atoms, alkoxyalkyl

6. A polyolefin composition according to claim 3, in which, in the compounds of the formula

(IIb), T is alkyl having 1 to 6 carbon atoms, T₁ is hydrogen, chlorine or alkyl having 1 to 4 carbon atoms, n is 1 or 2 and, if n is 1, T₂ is one of the radicals of the formula -OT₃ or



and, if n is 2, T₂ is a radical of the formula -O-T₉-O- or



in which T₃ is hydrogen, alkyl having 1 to 18 carbon atoms or alkyl which has 3 to 18 carbon atoms and is interrupted once or several times by -O-, T₄ and T₅ independently of one another are hydrogen, alkyl having 1 to 18 carbon atoms, alkenyl having 3 to 8 carbon atoms or hydroxyalkyl having 2 to 4 carbon atoms, T₆ is hydrogen or alkyl having 1 to 6 carbon atoms, and T₉ and T₁₀ are alkylene having 2 to 8 carbon atoms, alkenylene having 4 to 8 carbon atoms or alkylene which has 2 to 18 carbon atoms and is interrupted once or several times by -O-.

77. A polyolefin composition according to claim 3, in which, in the compounds of the formula (III), the substituents Y₁ are hydrogen, alkyl having 1 to 12 carbon atoms or halogen, if u is 1, Y₂ is alkyl having 1 to 18 carbon atoms, alkyl which has 1 to 12 carbon atoms and is substituted by hydroxyl, alkoxy having 1 to 18 carbon atoms, -COOY₈, -CONY₉Y₁₀ and/or -OCOY₁₁, glycidyl or phenylalkyl having 1 to 4 carbon atoms in the alkyl moiety, or, if u is 2, Y₂ is alkylene having 2 to 16 carbon atoms, alkenylene having 4 to 12 carbon atoms, xylene or alkylene which has 3 to 20 carbon atoms, is interrupted by one or more -O- atoms and/or is substituted by hydroxyl, the substituents Y₈ to Y₁₁ being as defined in claim 3.

8. A polyolefin composition according to claim 7, in which u is 1 and r is 2, Y₁ is alkyl having 1 to 4 carbon atoms and Y₂ is alkyl having 1 to 18 carbon atoms or alkyl which has 1 to 12 carbon atoms and is substituted by hydroxyl, alkoxy having 1 to 18 carbon atoms, -COOY₈ and/or -OCOY₁₁, Y₈ being alkyl having 1 to 18 carbon atoms, alkenyl having 3 to 18 carbon atoms or alkyl which has 3 to 20 carbon atoms, is interrupted by one or more oxygen atoms and/or is substituted by hydroxyl, and Y₁₁ being alkenyl having 2 to 18 carbon atoms.

9. A polyolefin composition according to claim 8, in which Y₁ is methyl and Y₂ is an octyl radical or alkyl which has 1 to 3 carbon atoms and is substituted by hydroxyl, alkoxy having 13 or 15 carbon atoms, -COOY₈ and/or -OCOY₁₁, Y₈ being a decyl or octadecenyl radical or alkyl which has 7 carbon atoms and is substituted by hydroxyl and interrupted by an oxygen atom, and Y₁₁ being propenyl.


10. A polyolefin composition according to claim 3, in which, in the compounds of the formula (I), v and w independently of one another are 1 or 2 and the substituents Z independently of one another are hydrogen, halogen or alkoxy having 1 to 12 carbon atoms.

11. A polyolefin composition according to claim 3, in which, in the compounds of the formula (IV), x and y are 1 or 2 and the substituents L independently of one another are hydrogen or alkyl having in each case 1 to 12 carbon atoms.

SUB
257
12. A polyolefin composition according to claim 1 wherein the amount of the individual UV absorber in the mixture is from 20% to 80% based on the weight of the mixture, with the proviso that the sum adds to 100%.

13. A polyolefin composition according to claim 1 wherein the total amount of UV-absorber is from 0.005 to 5% based on the weight of the polymer.

14. A polyolefin composition according to claim 1, which additionally contains at least one sterically hindered amine, in particular an amine of this type containing at least one radical of the formula



in which R is hydrogen or methyl.

15. The use of a mixture of UV-absorbers according to claim 1 for the stabilization of polyolefins.